

Amendment under 37 CFR § 1.116
Application No. 10/506,537
Attorney Docket No. 042541

RECEIVED
CENTRAL FAX CENTER
NOV 03 2006

AMENDMENTS TO THE CLAIMS

This listing of claims replaces all prior versions of claims in the application.

1. (Currently amended) A heat-resistant Ni-alloy composite having excellent high-temperature oxidation resistance, comprising:

a Ni-alloy substrate and

a multi-layer surface structure formed on the Ni-alloy substrate, the multi-layer surface structure being formed by Al-diffusing treatment of the Ni-alloy substrate containing Cr, or by Al-diffusing treatment of the Ni alloy substrate coated with a Cr-containing layer, comprising

an inner Cr layer with Cr content of more than 85 % composed of an α -Cr phase in the form of α -Cr phase composed of precipitates between the substrate and an outer layer and

an the outer layer composed of a β phase (Ni-Al-Cr) and a γ' phase (Ni₃Al(Cr)) on the substrate, wherein the Al content in the outer layer is at least 20 atomic percent.

2. (Currently amended) The heat-resistant Ni-alloy composite according to claim 1, wherein the ~~Ni alloy substrate comprises~~ Cr-containing layer is a Ni-Cr-based alloy layer.

3. (Currently amended) The heat-resistant Ni-alloy composite according to claim 1 and 2, wherein the ~~Ni-Cr-based alloy~~ Cr-containing layer has a Cr content of at least 20 atomic percent.

4. (Cancelled).

Amendment under 37 CFR § 1.116
Application No. 10/506,537
Attorney Docket No. 042541

5. (Original) The heat-resistant Ni-alloy composite according to claim 1, wherein the Ni-alloy substrate comprises a heat-resistant Ni-based alloy or a Ni-based superalloy.

6. (Original) The heat-resistant Ni-alloy composite according to claim 1, wherein the Ni-alloy substrate comprises a Ni-Cr-based alloy having a Cr content of at least 20 atomic percent.